TECHNICAL ADVISORY BULLETIN From North America's Largest Roofing Manufacturer! To: GAF Residential Sales, GAF Contractors, GAF Field Services Issued Date: 05/27/2011 From: Technical Services Department Issued Date: 05/27/2011 Subject: Corrosion Of Aluminum Gutters And Flashings Caused By Copper Revised Date: 06/01/2016 Granule Used In Algae Resistant Shingles No: TAB-R 2011-107	
GAF's Experience:	Based on our research, a few isolated incidents of galvanic reaction have been documented. In each case, the metal was determined to have been sourced from the same place and in both cases, standing water was evident. Aluminum is very susceptible to galvanic corrosion when contact with copper, assuming that the two metals are also in contact with moisture.
What's The Science?	When dissimilar metals are in contact with each other and in the presence of moisture, such as rainwater, a galvanic reaction occurs. This reaction results in the corrosion of the metal with the lower galvanic rating (in this case, the aluminum). Since copper has one of the highest galvanic rating or "nobility", it will not be harmed by interaction with the majority of other metals. However, it will bring about corrosion of the other metals (aluminum) if in direct contact.
Can You Expect To Have A Galvanic Reaction Between The Copper	Copper will cause deterioration of aluminum. The rate of this deterioration is a factor of the amount of time the two metals are in contact. In areas where algae resistant shingles are utilized for their benefits, many homeowners elect to use non-metallic gutters such as PVC.
Algae Resistant Shingle Granules And The Aluminum Gutters Or Flashings?	Copper granules have been used by the roofing industry for some time to provide algae resistance and anecdotal experience indicates that corrosion of aluminum gutters can be magnified when the gutters do not drain properly (e.g., are level and do not slope to the down spouts) allowing the accumulation of granules in the gutter. It would be difficult to speculate on whether any problems will occur, however, experience would indicate that if algae resistant shingles are combined with aluminum gutters, you can help to minimize potential problems by insuring that the gutters are free flowing, provide adequate slope to drain, and do not allow the accumulation of granules.
What Precautions Need To Be Taken?	As stated, the best preventative measure is adequate drainage of water. If water is left standing and granules build-up, the potential for deterioration increases.
What GAF Shingles Currently Have StainGuard® Protection?	 GAF Shingles With StainGuard[®] Protection Available Nationwide: All GAF Lifetime Designer Shingles except Grand Sequoia[®], Marquis WeatherMax[®], Timberline[®] American Harvest[®], Timberline Cool Series[®], Timberline[®] ArmorShield II[™] GAF Shingles With StainGuard[®] Protection Available In Select Areas: Grand Sequoia[®], Royal Sovereign[®], Timberline[®] Natural Shadow[®], Timberline HD[®], Timberline Ultra HD[®] NOTE: StainGuard[®] protection applies only to shingles with StainGuard[®]-labeled packaging. See GAF Shingle & Accessory Ltd. Warranty for complete coverage and restrictions.
Where Can I Get More Information?	GAF Technical Services Can Assist You with these and other questions you may have regarding your new roof installation. GAF Technical Services can be contacted at 800-ROOF-411 (800-766-3411). Also, the GAF website is a great resource for just about any question you may have or for additional information you may require. Please visit <u>www.gaf.com</u> to find the latest information on our products and their installation.
	Important: This document supersedes any prior GAF Technical Advisory Bulletins on this topic. Please always check <u>www.gaf.com</u> to make sure you have the most up to date information.